

# Markant semi-gloss



HARDWAX OIL



## Even degree of gloss and full appearance

Natural hardwaxoil. High-quality, layer-building oils accentuate the natural look of the wood and at the same time achieve excellent resistance to dirt and water.

- Film-forming, wear-resistant
- Smooth and full bodied appearance
- Water and dirt resistant
- Easy and safe application
- Accentuates the natural beauty of the wood
- Certified anti-slip properties as per DIN EN 16165:2021-12 for work areas
- Suitable for children's toys as per EN 71-3

## Range of use:

Suitable for parquet, wood and cork floors. Anti-slip as per DIN EN 16165:2021-12 evaluation group R10. Suitable for virtually all types of European and exotic timber. Note the LOBA wood types list, which can be found at [www.loba.de](http://www.loba.de). If in doubt, consult the factory.



## Technical Data

ART.-NO.			
	750 ml	6	480
10508	2.5l	4	120
	10l	-	42

<b>Solids</b>	47.4 ±2%
<b>Contents</b>	aliphatic hydrocarbons, cobalt-free siccatives, vegetable waxes, siccatives
<b>Storage and transportation</b>	36 months of storage stability. No hazardous material according to ADR. Not sensitive to frost.
<b>GISCODE</b>	Ö60
<b>2004/42/CE</b>	EU limit value for this product (cat. A/i): 500 g/l (2010). This product contains max. 461 g/l VOC.

## Application

- The surface must be professionally sanded. The floor must be dry and free of any old coatings, oil, grease, wax, silicone, sanding dust and other impurities.
- The optimal processing conditions are room temperature +15°C to + 25°C, floor temperature +15°C to +22°C, rel. humidity 40% - 65%, material temperature +18°C - + 25°C, max. wood moisture 12%, sufficiently ventilate working rooms.
- In order to prevent parquet damage, the room temperature should be set to the annual average expected for the use of the product.
- Transfer material to a LOBA varnish bucket before applying.
- Shake the contents well.
- Observe general and, if necessary, product-specific occupational health and safety regulations. Further information can be found in the GISCODE-related operating instructions which are available under [www.wingis-online.de](http://www.wingis-online.de).
- This product is part of the LOBA and Wakol "Connected Systems". The approved combinations with Wakol parquet adhesives may be found in the "Connected Systems" Matrix: [www.loba.de/connected-systems](http://www.loba.de/connected-systems)

### THINNER / MIXING

The product is ready for use and must not be reduced!

### APPLICATION TOOL / APPLICATION RATE

Trowel application: LOBA trowel / approx. 20 ml/m<sup>2</sup> (50 m<sup>2</sup>/l)  
roller and brush application: LOBA oil roller Microfaser 60-80 or LOBA oilbrush / approx. 60-100 ml/m<sup>2</sup> (12m<sup>2</sup>/l)

### DRYING TIME

- Earliest possible overcoating after 12 hours.
- However within 24 hours.
- Can be walked on after 12 hours.
- Light stress after 24 hours.
- Full Stress and coverage after 10 days.
- The floor can be covered earlier by using LOBA Cover 400, for details see the TI for the product.

### TROWEL AND ROLLER APPLICATION:

- Carefully apply Markant in sections using a LOBA trowel.
- Immediately equalise with a single-disc machine and the LOBASAND SpecialPad beige underneath.
- Dry overnight, maximum 24 hours.
- Roll on a thin and even layer of Markant using the LOBA oil roller Microfaser 60-80.

### ROLLER APPLICATION:

- Apply a thin and even layer of Markant using the LOBA oil roller Microfaser 60-80/LOBA oilbrush.
- Dry overnight, maximum 24 hours.
- If necessary (uneven appearance or matt / gloss areas), perform and intermediate sanding and remove any dust.
- Apply a thin and even layer of Markant using the LOBA oil roller Microfaser 60-80/LOBA oilbrush.

### PREPARATION OF CORK COVERINGS

The adhesive must be fully released (note the adhesive manufacturer's instructions), the surface must be dry and free of any soiling or adhesive residue.

If necessary, finely sand homogeneous cork coverings and carefully remove any cork dust (vacuum)

### TREATMENT OF HOMOGENEOUS / SOLID CORK FLOORING:

Apply a thin layer of Markant. Dry overnight. Apply a thin layer of Markant. The drying time until a tack-free surface is achieved can, depending on the climate conditions in the room, take up to 3 days

### TREATMENT OF VENEERED CORK FLOORING

Apply a thin layer of Markant. Dry for at least 48 hours. Carry out wax care with LOBA NatureWax or LOBA ParkettWax.

### IMPORTANT INFORMATION

Excess material must be completely removed during equalisation. Drying delays are possible on some exotic timbers.

Trowel applications are only possible with joint-sealed wooden flooring. Oil that penetrates joints will not dry completely over a long period.

Keep soaked cloths, pads and other tools in closed containers. Moisten oil in combination with sanding dust, fabric cloths and so on with water or store in a sealable bucket and dispose of in a fire-safe manner, since otherwise there is a risk of self-ignition.

## General guidelines

**Cleaning of tools:** Clean tools with solvents such as brush cleaner.

**Drying time:** The indicated drying times are valid for +20°C and 50% relative humidity, and assume careful, draught-free ventilation of the working area. Lower temperatures, higher relative humidity or poorer ventilation lead to longer drying times. Do not apply any protective coverings, wet clean the surface or lay carpet until the coating has achieved its final hardening. Product-specific data can be found in the relevant technical information.

**Side bonding:** Parquet that has not been shear-resistently bonded in place, wood planks, wooden pavings, industrial parquet and parquet on underfloor heating as well as types of wood with a short moisture changing times (e.g. beech) show dimensional changes caused by quickly varying climate (rel. air humidity, temperature). When applying oil side bonding and thus unregular cracks in joints can not appear.

**Interactions:** Materials such as carpet underlays, furniture legs, castors, flexible adhesives used for parquet or for fixing can lead to softening and discoloration. Material building up in the joints can adversely affect touch and appearance. Exposure to hair dyes or rubber tyres on cars, motorcycles and cycles can lead to permanent, irreversible discoloration of the surface.

**Safety notes:** Flammable solvent vapours emerge during the drying process when working with products containing high quantities of solvents. As a result, fire, naked light, welding, smoking and so on are prohibited in the immediate vicinity of such products. Ventilate working areas and storage rooms well. Electrical equipment in workrooms and ancillary rooms must be switched off in sufficient time to ensure that they are cold when work begins. Any spark generation, including on electrical equipment, must be avoided. Keep material containers tightly closed. Solvent sensitive components, plants or animals (fish tanks) must be removed from areas at risk of exposure to solvent vapours.

**Connected Systems:** Connected Systems approved products are optimized in such way that no dark discoloration, caused by chemical interaction between surfacetreatment and adhesive occurs, when applied in accordance with the technical datasheets.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and relate to Spezial conditions. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice by speaking to the LOBA application engineering department. Observe the floor covering manufacturer's recommendations and the provisions of the current standards. Our liabilities and responsibilities are exclusively in accordance with our Terms and Conditions and are not extended by this information or by our advice. The publishing of a new technical data sheet automatically invalidates the earlier version.

The words or symbols denoted by ® stand for trademark rights that are at least registered and protected in the territory of Germany.